

Specification Sheet

NaturaSeal 200R Nonwoven Geotextile

Naturaseal 200R is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers. Naturaseal 200R resists ultraviolet deterioration, rotting, biological degradation, naturally encountered bases and acids. Polypropylene is stable within a pH range of 2 to 13.

Roll Size:

6" x 360' / 12" x 360' / 24" x 360' / 45" x 360' / 70" x 360'

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Tensile Strength	ASTM D4632	N	445
Grab Elongation	ASTM D4632	%	50
Tear Resistance	ASTM D4533	N	200
CBR Puncture ¹	ASTM D6241	N	1320
Permittivity	ASTM D4491	sec ⁻¹	2.0
Water Flow Rate	ASTM D4491	l/min/m ²	6095
Apparent Opening Size	ASTM D4751	mm	0.300
UV Stability	ASTM D4355	% @ 500h	70

1. Burst strength (Mullen ASTM D3786) and Puncture (ASTM D4833) are both replaced by CBR Puncture (ASTM D6241) *All values are MARV except where specified.